

Resist:	AZ MIR 701 29cps	Recipe:	Labspin 6 - quick, acc: 1000, 30s, bake 60s@90°C
Substrate:	4" ssp Si wafer (coater dummies)	Measurement:	9 point on Filmtek
Tester:	TARAN	Test date:	02-06-2021

rpm	Average thickness [nm]	Deviation [nm]	Uniformity %	EBR [mm]
1000	2830	20	1	5
2000	1810	10	0,63	2
3000	1470	5	0,51	1
5000	1200	5	0,48	0
8000	990	10	0,82	0

