

Resist: AZ 4562 **Recipe:** Labspin 6 - quick, acc: 2000, 60s, bake 60s@100°C

Substrate: 4" ssp Si wafer fresh from the box **Measurement:** 9 point on Ellipsometer VASE

Tester: LGPE **Test date:** 12. Jan 2017

rpm	Thickness [nm]									Uniformity %
2000	9529,86	9162,47	9177,89	9223,57	9160,71	9068,56	8968,44	9335,95	9151,61	3,03
3000	7672,08	7354,65	7425,58	7439,21	7363,83	7297,28	7284,52	7263,16	7242,25	2,88
3000	7632,96	7318,95	7397,78	7326,46	7282,87	7096,14	7144,9	7072,12	7009,21	4,26
4000	6672,7	6405,76	6416,58	6418,62	6376,37	6300,22	6284,14	6298,15	6264,92	3,15
4000	6715,7	6449,34	6443,54	6485,64	6475,36	6127,64	6269,35	6494,54	6297,86	4,58
5000	6110,34	5849,66	5843,92	5830,72	5795,59	5743,86	5816,31	5699,13	5686,61	3,59
5000	6091,75	5862,84	5708,73	5836,96	5842,28	5915,76	5681,89	5664,69	5733,66	3,63

