

Fox-15

Recipe:

Prebake:

Prebake 5 min 220C

Spinning:

Speed: xxx rpm, Acceleration 4000 rpm/s, 60 s spinning time

Soft bake:

Post spinning bake 2 min 120C, Post spinning bake 2 min 220C

speed [rpm]	Thickness [nm]
3000	445
4000	420
5000	401
6000	388

